

have now completed the administrative review in accordance with section 751 of the Act.

Scope of the Review

For purposes of this administrative review, the products covered are certain stainless steel sheet and strip in coils. Stainless steel is an alloy steel containing, by weight, 1.2 percent or less of carbon and 10.5 percent or more of chromium, with or without other elements. The subject sheet and strip is a flat-rolled product in coils that is greater than 9.5 mm in width and less than 4.75 mm in thickness, and that is annealed or otherwise heat treated and pickled or otherwise descaled. The subject sheet and strip may also be further processed (e.g., cold-rolled, polished, aluminized, coated, etc.) provided that it maintains the specific dimensions of sheet and strip following such processing.

The merchandise subject to this order is currently classifiable in the *Harmonized Tariff Schedule of the United States* ("HTS") at subheadings:

7219.13.0031, 7219.13.0051,
7219.13.0071, 7219.1300.81²,
7219.14.0030, 7219.14.0065,
7219.14.0090, 7219.32.0005,
7219.32.0020, 7219.32.0025,
7219.32.0035, 7219.32.0036,
7219.32.0038, 7219.32.0042,
7219.32.0044, 7219.33.0005,
7219.33.0020, 7219.33.0025,
7219.33.0035, 7219.33.0036,
7219.33.0038, 7219.33.0042,
7219.33.0044, 7219.34.0005,
7219.34.0020, 7219.34.0025,
7219.34.0030, 7219.34.0035,
7219.35.0005, 7219.35.0015,
7219.35.0030, 7219.35.0035,
7219.90.0010, 7219.90.0020,
7219.90.0025, 7219.90.0060,
7219.90.0080, 7220.12.1000,
7220.12.5000, 7220.20.1010,
7220.20.1015, 7220.20.1060,
7220.20.1080, 7220.20.6005,
7220.20.6010, 7220.20.6015,
7220.20.6060, 7220.20.6080,
7220.20.7005, 7220.20.7010,
7220.20.7015, 7220.20.7060,
7220.20.7080, 7220.20.8000,
7220.20.9030, 7220.20.9060,
7220.90.0010, 7220.90.0015,
7220.90.0060, and 7220.90.0080.

Although the HTS subheadings are provided for convenience and customs purposes, the Department's written

description of the merchandise under review is dispositive.

Excluded from the review of this order are the following: (1) sheet and strip that is not annealed or otherwise heat treated and pickled or otherwise descaled, (2) sheet and strip that is cut to length, (3) plate (i.e., flat-rolled stainless steel products of a thickness of 4.75 mm or more), (4) flat wire (i.e., cold-rolled sections, with a prepared edge, rectangular in shape, of a width of not more than 9.5 mm), and (5) razor blade steel. Razor blade steel is a flat-rolled product of stainless steel, not further worked than cold-rolled (cold-reduced), in coils, of a width of not more than 23 mm and a thickness of 0.266 mm or less, containing, by weight, 12.5 to 14.5 percent chromium, and certified at the time of entry to be used in the manufacture of razor blades. See chapter 72 of the HTS, "Additional U.S. Note" 1(d).

Flapper valve steel is also excluded from the scope of the order. This product is defined as stainless steel strip in coils containing, by weight, between 0.37 and 0.43 percent carbon, between 1.15 and 1.35 percent molybdenum, and between 0.20 and 0.80 percent manganese. This steel also contains, by weight, phosphorus of 0.025 percent or less, silicon of between 0.20 and 0.50 percent, and sulfur of 0.020 percent or less. The product is manufactured by means of vacuum arc remelting, with inclusion controls for sulphide of no more than 0.04 percent and for oxide of no more than 0.05 percent. Flapper valve steel has a tensile strength of between 210 and 300 ksi, yield strength of between 170 and 270 ksi, plus or minus 8 ksi, and a hardness (Hv) of between 460 and 590. Flapper valve steel is most commonly used to produce specialty flapper valves in compressors.

Also excluded is a product referred to as suspension foil, a specialty steel product used in the manufacture of suspension assemblies for computer disk drives. Suspension foil is described as 302/304 grade or 202 grade stainless steel of a thickness between 14 and 127 microns, with a thickness tolerance of plus-or-minus 2.01 microns, and surface glossiness of 200 to 700 percent Gs. Suspension foil must be supplied in coil widths of not more than 407 mm, and with a mass of 225 kg or less. Roll marks may only be visible on one side, with no scratches of measurable depth. The material must exhibit residual stresses of 2 mm maximum deflection, and flatness of 1.6 mm over 685 mm length.

Certain stainless steel foil for automotive catalytic converters is also excluded from the scope of this order. This stainless steel strip in coils is a

specialty foil with a thickness of between 20 and 110 microns used to produce a metallic substrate with a honeycomb structure for use in automotive catalytic converters. The steel contains, by weight, carbon of no more than 0.030 percent, silicon of no more than 1.0 percent, manganese of no more than 1.0 percent, chromium of between 19 and 22 percent, aluminum of no less than 5.0 percent, phosphorus of no more than 0.045 percent, sulfur of no more than 0.03 percent, lanthanum of less than 0.002 or greater than 0.05 percent, and total rare earth elements of more than 0.06 percent, with the balance iron.

Permanent magnet iron-chromium-cobalt alloy stainless strip is also excluded from the scope of this order. This ductile stainless steel strip contains, by weight, 26 to 30 percent chromium, and 7 to 10 percent cobalt, with the remainder of iron, in widths 228.6 mm or less, and a thickness between 0.127 and 1.270 mm. It exhibits magnetic remanence between 9,000 and 12,000 gauss, and a coercivity of between 50 and 300 oersteds. This product is most commonly used in electronic sensors and is currently available under proprietary trade names such as "Arnokrome III."³

Certain electrical resistance alloy steel is also excluded from the scope of this order. This product is defined as a non-magnetic stainless steel manufactured to American Society of Testing and Materials (ASTM) specification B344 and containing, by weight, 36 percent nickel, 18 percent chromium, and 46 percent iron, and is most notable for its resistance to high temperature corrosion. It has a melting point of 1390 degrees Celsius and displays a creep rupture limit of 4 kilograms per square millimeter at 1000 degrees Celsius. This steel is most commonly used in the production of heating ribbons for circuit breakers and industrial furnaces, and in rheostats for railway locomotives. The product is currently available under proprietary trade names such as "Gilphy 36."⁴

Certain martensitic precipitation-hardenable stainless steel is also excluded from the scope of this order. This high-strength, ductile stainless steel product is designated under the Unified Numbering System (UNS) as S45500-grade steel, and contains, by weight, 11 to 13 percent chromium, and 7 to 10 percent nickel. Carbon, manganese, silicon and molybdenum each comprise, by weight, 0.05 percent

Zanesville Armco Independent Organization Inc., and the United Steelworkers of America, AFL-CIO/CLC.

²Due to changes to the HTS numbers in 2001, 7219.13.0030, 7219.13.0050, 7219.13.0070, and 7219.13.0080 are now 7219.13.0031, 7219.13.0051, 7219.13.0071, and 7219.13.0081, respectively.

³"Arnokrome III" is a trademark of the Arnold Engineering Company.

⁴"Gilphy 36" is a trademark of Imphy, S.A.